

## TEST REPORT No 89134 A

1. Customer, its address **Printful Latvia JSC, 6B Ojara Vaciesa, LV-1004, Latvia**
2. Sample identification according to the announcement No L-18718  
 Product name **Fabric #64034 94% PES 6% EL**  
 Sample size **119 x 119 cm**
3. Sample description  
**Black colored fabric with label: Fabric #64034 94% PES 6% EL**
4. Testing time  
 Received **01/07/2020**      Started **01/07/2020**      Finished **09/07/2020**
5. Test results and methods

Parameter tested	Test result	Test method
Formaldehyde	Not detected	LVS EN ISO 14184-1:2011
pH, 20°C	6.6	LVS EN ISO 3071:2006
Air permeability	67±13 L/m <sup>2</sup> ·s	LVS EN ISO 9237:2001 (100 Pa)
Abrasion resistance	> 50 000 rubs	LVS EN ISO 12947-2:2017 (Nominal test pressure 9 kPa)
Color fastness to dry rubbing:		LVS EN ISO 105-X12:2016
- the numerical grey scale rating for staining	4-5	
Color fastness to wet rubbing:		LVS EN ISO 105-X12:2016
- the numerical grey scale rating for staining	5	



N. Mils  
Laboratory Head Deputy  
09/07/2020