

**TEST REPORT No 88367 A**

1. Customer, its address **Printful Latvia JSC, 6B Ojara Vaciesa, LV-1004, Latvia**
2. Sample identification according to the announcement No L-18374  
Product name **Fabric #34456 96% PES 4% EL**  
Sample size **1.20 x 1.20 m**
3. Sample description **Black colored fabric with label: Audums #34456 96% PES 4% EL**
4. Testing time  
Received **13/03/2020** Started **18/03/2020** Finished **24/03/2020**

## 5. Test results and methods

Parameter tested	Test result	Test method
Formaldehyde	Not detected	LVS EN ISO 14184-1:2011
pH, 20°C	6.4	LVS EN ISO 3071:2006
Air permeability	73±15 L/m <sup>2</sup> ·s	LVS EN ISO 9237:2001 (100 Pa)
Abrasion resistance	> 50 000 rubs	LVS EN ISO 12947-2:2017 (Nominal test pressure 9 kPa)
Color fastness to dry rubbing:		LVS EN ISO 105-X12:2016
- the numerical grey scale rating for staining	3-4	
Color fastness to wet rubbing:		LVS EN ISO 105-X12:2016
- the numerical grey scale rating for staining	4-5	

Z. Veseris  
Laboratory Manager  
25/03/2020