

Test Report

No.: TJHL1906003063CW

Date: JUL.16, 2019

Page: 1 of 6

PHOTO USA ELECTRONIC GRAPHIC INC.

8 DONGDAQIAO ROAD, STE, 2716, THE SPACES INT'L CENTER

The following sample(s) was/were submitted and identified by the client as:

Sample Description : 11OZ TWO TONE MUG-INNER&HANDLE COLOR LIGHT
BLUE

Supplier : PHOTO USA

Manufacture : PHOTO USA

Country of Origin : CHINA

Sample Receiving Date : JUN.24, 2019

Testing Period : JUN.24, 2019 TO JUL.16, 2019

Test Performed : SELECTED TEST(S) AS REQUESTED BY APPLICANT

Test Requested : PLEASE REFER TO THE RESULT SUMMARY.

Test Result(s) : FOR FURTHER DETAILS, PLEASE REFER TO THE
FOLLOWING PAGE(S)

Test Summary :

Test Requested	Conclusion
EN 15284: 2007 MATERIAL AND ARTICLES IN CONTACT WITH FOOD STUFFS - TEST METHOD FOR THE RESISTANCE TO MICROWAVE HEATING OF CERAMIC, GLASS, GLASS-CERAMIC OR PLASTICS COOKWARE	PASS

Signed for and on behalf of
SGS-CSTC Standards Technical Services (Tianjin) Co., Ltd.

Michael



Michael Wen
Authorized Signatory



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

Building C-9, No.80, Haiyun Avenue, TEDA, Tianjin, China 300457 t(86-22) 59995061
中国·天津·经济技术开发区海云街80号C-9厂房 邮编: 300457 t(86-22) 59995061

www.sgs.com
sgs.china@sgs.com

Test Report

No.: TJHL1906003063CW

Date: JUL.16, 2019

Page: 2 of 6

Test Conducted:

EN 15284: 2007 Material and articles in contact with food stuffs - Test method for the resistance to microwave heating of ceramic, glass, glass-ceramic or plastics cookware

1) Scope: The European Standard specifies a method for the determination of the resistance to microwave heating of cookware made of ceramic, glass, glass – ceramic or plastics.

It is applicable to articles that are intended for multiple re-use in a microwave oven. It is not applicable to articles, particularly those made from plastics, which are intended to be discarded after one use.

2) Product Category: Ceramic

3) Number of tested sample: 4 pieces

4) Procedure

Clause	Test item	Test method/Requirement
5.1	Determination of power output	<p>At the start of the test ensure that the oven is at ambient temperature of $(20 \pm 3) ^\circ\text{C}$, and measure that temperature. Add $1000 \text{ g} \pm 5 \text{ g}$ of water to the container and determine its actual mass. Cool the container and water to $(5 \pm 1) ^\circ\text{C}$ below ambient temperature. Stir the water, measure its temperature and immediately place the container in the centre of the oven on the turntable at its lowest normal position. Operate the oven until a temperature $(5 \pm 1) ^\circ\text{C}$ above ambient temperature is obtained and record the time of operation. Measure the temperature of the water and container within 60 s of the oven being switched off.</p> <p>The microwave power output shall be calculated using the following equation:</p> $P = \frac{4,187 \times \Delta T}{t} (m_w + 0.55m_c)$ <p>Where</p> <p>P is the microwave power output in Watts;</p> <p>ΔT is the difference between the initial and final water temperature;</p> <p>t is the time in seconds;</p> <p>m_w is the mass of water in grams;</p> <p>m_c is the mass of the container in grams.</p>



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

Building C-9, No.80, Haiyun Avenue, TEDA, Tianjin, China 300457 t(86-22) 59995061
 中国·天津·经济技术开发区海云街80号C-9厂房 邮编: 300457 t(86-22) 59995061

www.sgsgroup.com.cn
sgs.china@sgs.com

Test Report

No.: TJHL1906003063CW

Date: JUL.16, 2019

Page: 3 of 6

Clause	Test item	Test method/Requirement
5.2	Determination of heating time	Once the power output has been determined, calculate the times needed to give an energy value of 72 000 J for the short period and 468 000 J for the long period of test using the following equation: $t = E/P$ Where t is the time required in seconds; P is the microwave power output in Watts; E is the energy required in Joules.
6.1	Testing of product	Apply a stain to the surface of the test specimen and wash clear.
6.2		Visually check that the surface is not damaged. Note any small faults (e.g. pinholes in the glaze) prior to testing.
6.3		Except for articles made from glass or glass-ceramic, immerse the test specimen in water at a temperature of $(20 \pm 3) ^\circ\text{C}$ for one hour and then wipe the surface dry with a cloth.
6.4		Pour (125 ± 2.5) ml of water into each water container and place at the back of the oven so as not to interfere with the turntable.
6.5		Place the test specimen at the centre of the oven on the turntable and microwave for the time determined in 5.2 to apply the specified energy for the short period. If electrical arcing begins IMMEDIATELY SWITCH OFF THE OVEN. Terminate the test and state in the test report that at the onset of electrical arcing the test was terminated.
6.6		After the cycle is completed, open the oven door and, if applicable, using the surface temperature measuring apparatus, find and record the highest temperature of the handle. When additional data is required, follow this procedure to find the highest surface temperature. Ensure that this process takes no longer than 45 s.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

Building C-9, No.80, Haiyun Avenue, TEDA, Tianjin, China 300457 t(86-22) 59995061
中国·天津·经济技术开发区海云街80号C-9厂房 邮编: 300457 t(86-22) 59995061

www.sgs.com
sgs.china@sgs.com

Test Report

No.: TJHL1906003063CW

Date: JUL.16, 2019

Page: 4 of 6

Clause	Test item	Test method/Requirement
6.7		Immediately following 6.6, set the oven for the long period determined in 5.2 and restart.
6.8		After completion, when additional data is required, record the highest surface temperature (in no more than 45 s). Remove the test specimen from the oven and allow it to cool on an insulated surface to prevent thermal shock.
6.9		Apply stain to the test specimen and wash clear (as in 6.1).
6.10		Visually inspect the test specimen for damage according to the criteria in Table 1.
6.11		Repeat the test using the different article shapes in the set.

5) Test result:

For short heating period:

	Sample 1	Sample 2	Sample 3
The maximum handle temperature	36.2°C	37.1°C	36.9°C
Damage	Pass	Pass	Pass
Arcing	Pass	Pass	Pass
Temperature limits	56°C	56°C	56°C

The maximum surface temperature of handles after the short period heating shall not exceed the following limit values:

ceramic, glass-ceramic or glass: 56°C;

plastics: 60°C.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

Building C-9, No.80, Haiyun Avenue, TEDA, Tianjin, China 300457 t(86-22) 59995061
中国·天津·经济技术开发区海云街80号C-9厂房 邮编: 300457 t(86-22) 59995061

www.sgsgroup.com.cn
sgs.china@sgs.com

Test Report

No.: TJHL1906003063CW

Date: JUL.16, 2019

Page: 5 of 6

For long heating period:

	Sample 1	Sample 2	Sample 3
Damage	Pass	Pass	Pass
Arcing	Pass	Pass	Pass

Note:

Table 1 – Inspection criteria

Material	Cracking	Crazing	Scaling	Colour	Melting	Deform action	Suitability for re-use	Charring
Ceramic	+	+(a)	+(b)	+(c)				
Glass, glass-ceramic	+		+(b)	+(c)				
Plastics	+			+(c)	+(d)	+	+(e)	+
(+) = to be inspected a refers to the glaze b refers to on-glaze decoration c if several colours are present on one article to be inspected, the colour with the greatest change shall be chosen d article shall not be too soft to handle e article shall be washable and stain resistant								

Remark:

Pass = No damage, arcing was found and the highest temperature for each item was within the temperature limit.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

Building C-9, No.80, Haiyun Avenue, TEDA, Tianjin, China 300457 t(86-22) 59995061
 中国·天津·经济技术开发区海云街80号C-9厂房 邮编: 300457 t(86-22) 59995061

www.sgs.com
sgs.china@sgs.com


Test Report

No.: TJHL1906003063CW

Date: JUL.16, 2019

Page: 6 of 6

Sample Photo:



SGS authenticate the photo on original report only

End of Report



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

Building C-9, No.80, Haiyun Avenue, TEDA, Tianjin, China 300457 t (86-22) 59995061
中国·天津·经济技术开发区海云街80号C-9厂房 邮编: 300457 t (86-22) 59995061

www.sgsgroup.com.cn
sgs.china@sgs.com