

TEST REPORT No 88371 A1. Customer, its address **Printful Latvia JSC, 6B Ojara Vaciesa, LV-1004, Latvia**

2. Sample identification according to the announcement No L-18374

Product name **Fabric #10853 100% PES**Sample size **1.20 x 1.20 m**

3. Sample description


Black colored fabric with label: Audums #10853 100% PES

4. Testing time

Received
13/03/2020Started
18/03/2020Finished
25/03/2020

5. Test results and methods

Parameter tested	Test result	Test method
Formaldehyde	Not detected	LVS EN ISO 14184-1:2011
pH, 20°C	6.5	LVS EN ISO 3071:2006
Air permeability	435±87 L/m ² ·s	LVS EN ISO 9237:2001 (100 Pa)
Abrasion resistance	> 50 000 rubs	LVS EN ISO 12947-2:2017 (Nominal test pressure 9 kPa)
Color fastness to dry rubbing:		LVS EN ISO 105-X12:2016
- the numerical grey scale rating for staining	4	

Z. Veseris
Laboratory Manager
26/03/2020