

TEST REPORT No 88363 A

1. Customer, its address **Printful Latvia JSC, 6B Ojara Vaciesa, LV-1004, Latvia**
2. Sample identification according to the announcement No L-18374
Product name **Knitted fabric #26102 82% PES 18% EL**
Sample size **1.20 x 1.20 m**
3. Sample description **Black colored knitted fabric with label: Trikotāža #26102 82% PES 18% EL**
4. Testing time
Received **13/03/2020** Started **18/03/2020** Finished **20/03/2020**
5. Test results and methods

| Parameter tested | Test result | Test method |
|--|----------------------------|--|
| Formaldehyde | Not detected | LVS EN ISO 14184-1:2011 |
| pH, 20°C | 6.1 | LVS EN ISO 3071:2006 |
| Air permeability | 263±53 L/m ² ·s | LVS EN ISO 9237:2001 (100 Pa) |
| Abrasion resistance | > 50 000 rubs | LVS EN ISO 12947-2:2017 (Nominal test pressure 9 kPa) |
| Color fastness to dry rubbing: | | LVS EN ISO 105-X12:2016 |
| - the numerical grey scale rating for staining | 4-5 | |
| Color fastness to wet rubbing: | | LVS EN ISO 105-X12:2016 |
| - the numerical grey scale rating for staining | 4-5 | |



Z. Veseris
Laboratory Manager
23/03/2020