

TEST REPORT No 89133 A

1. Customer, its address **Printful Latvia JSC, 6B Ojara Vaciesa, LV-1004, Latvia**
2. Sample identification according to the announcement No L-18718
Product name **Fabric #138650 100% PES**
Sample size **119 x 119 cm**
3. Sample description
Printed black colored fabric with label: Fabric #138650 100% PES
4. Testing time
Received **01/07/2020** Started **01/07/2020** Finished **09/07/2020**
5. Test results and methods

Parameter tested	Test result	Test method
Formaldehyde	Not detected	LVS EN ISO 14184-1:2011
pH, 20°C	7.0	LVS EN ISO 3071:2006
Air permeability	299±60 L/m ² ·s	LVS EN ISO 9237:2001 (100 Pa)
Abrasion resistance	7000±1000 rubs	LVS EN ISO 12947-2:2017 (Nominal test pressure 9 kPa)
Color fastness to dry rubbing:		LVS EN ISO 105-X12:2016
- the numerical grey scale rating for staining	4-5	



N.Miles
Laboratory Head Deputy
09/07/2020