

**TEST REPORT No 88368 A**

1. Customer, its address **Printful Latvia JSC, 6B Ojara Vaciesa, LV-1004, Latvia**
2. Sample identification according to the announcement No L-18374  
Product name **Fabric #26962 100% PES**  
Sample size **1.20 x 1.20 m**
3. Sample description **Black colored fabric with label: Audums #26962 100% PES**
4. Testing time  
Received **13/03/2020** Started **18/03/2020** Finished **24/03/2020**

## 5. Test results and methods

Parameter tested	Test result	Test method
Formaldehyde	Not detected	LVS EN ISO 14184-1:2011
pH, 20°C	5.9	LVS EN ISO 3071:2006
Abrasion resistance	> 50 000 rubs	LVS EN ISO 12947-2:2017 (Nominal test pressure 9 kPa)
Color fastness to dry rubbing:		LVS EN ISO 105-X12:2016
- the numerical grey scale rating for staining	4	
Color fastness to wet rubbing:		LVS EN ISO 105-X12:2016
- the numerical grey scale rating for staining	3-4	
Tensile properties strip method Force:		LVS EN ISO 13934-1:2013 (gauge length 200 mm, rate of extension 100 mm/min, pretension 5 N)
- warp	1434±143 N	
- weft	2042±204 N	
Tensile properties strip method Elongation:		LVS EN ISO 13934-1:2013 (gauge length 200 mm, rate of extension 100 mm/min, pretension 5 N)
- warp	28.9±2.9%	
- weft	33.5±3.4%	

Z. Vesperis  
Laboratory Manager  
25/03/2020