

TEST REPORT No 88369 A

1. Customer, its address **Printful Latvia JSC, 6B Ojara Vaciesa, LV-1004, Latvia**
2. Sample identification according to the announcement No L-18374
 Product name **Fabric #11827 100% PES**
 Sample size **1.20 x 1.20 m**
3. Sample description **Black colored fabric with label: Audums #11827 100% PES**
4. Testing time
 Received **13/03/2020** Started **18/03/2020** Finished **24/03/2020**

5. Test results and methods

Parameter tested	Test result	Test method
Formaldehyde	Not detected	LVS EN ISO 14184-1:2011
pH, 20°C	5.9	LVS EN ISO 3071:2006
Abrasion resistance	> 50 000 rubs	LVS EN ISO 12947-2:2017 (Nominal test pressure 9 kPa)
Color fastness to dry rubbing:		LVS EN ISO 105-X12:2016
- the numerical grey scale rating for staining	4-5	
Tensile properties strip method Force:		LVS EN ISO 13934-1:2013 (gauge length 200 mm, rate of extension 100 mm/min, pretension 5 N)
- warp	1725±173 N	
- weft	2176±218 N	
Tensile properties strip method Elongation:		LVS EN ISO 13934-1:2013 (gauge length 200 mm, rate of extension 100 mm/min, pretension 5 N)
- warp	36.4±3.6%	
- weft	50.8±5.1%	



Z. Veseris
 Laboratory Manager
 25/03/2020