

**TEST REPORT No 88365 A**

1. Customer, its address **Printful Latvia JSC, 6B Ojara Vaciesa, LV-1004, Latvia**
2. Sample identification according to the announcement No L-18374  
Product name **Knitted fabric #42754 70% PES 27% CO 3% EL**  
Sample size **1.20 x 1.20 m**
3. Sample description  
**Black colored knitted fabric with label: Trikotāža #42754 70% PES 27% CO 3% EL**
4. Testing time  
Received **13/03/2020** Started **18/03/2020** Finished **23/03/2020**
5. Test results and methods

Parameter tested	Test result	Test method
Formaldehyde	Not detected	LVS EN ISO 14184-1:2011
pH, 20°C	6.5	LVS EN ISO 3071:2006
Air permeability	323±65 L/m <sup>2</sup> ·s	LVS EN ISO 9237:2001 (100 Pa)
Abrasion resistance	> 50 000 rubs	LVS EN ISO 12947-2:2017 (Nominal test pressure 9 kPa)
Color fastness to dry rubbing:		LVS EN ISO 105-X12:2016
- the numerical grey scale rating for staining	4-5	



Z. Veseris  
Laboratory Manager  
23/03/2020